

## TECHNICAL DATA SHEET

TDS: CVW4624A

### LUMINOUS PAINT CLEAR PROTECTIVE

255/W462

#### DESCRIPTION:

Coo-Var Luminous Paint Clear Protective is a clear coating essential to protect Coo-Var luminous paint against wear.

#### RECOMMENDED USE:

Coo-Var Luminous Paint Clear Protective can be used to protect the performance of Coo-Var Luminous Paint.

#### AVAILABILITY:

0.5 litre, 2.5 litre

#### FINISH:

Gloss

#### COLOUR:

Clear

#### TYPICAL S.G. (SPECIFIC GRAVITY):

1.05 @ 20 °C

#### VOLUME SOLIDS:

38%

#### WET FILM THICKNESS W.F.T

70 microns

#### DRY FILM THICKNESS D.F.T

25 to 30 microns

#### EXPECTED SPREADING RATE:

14 sq.m / litre

@ 30 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

#### TYPICAL VISCOSITY:

3.5 Poise @ 25 °C

#### FLASH POINT:

Non-flammable

#### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 45 mins @ 20 °C

Hard dry: 4 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

#### MINIMUM OVERCOATING TIME:

6 hours @ 20 deg C

#### APPLICATION SPECIAL CONDITIONS:

N/A

#### VOC CONTENT:

Max 50 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

#### APPLICATION DETAILS:

Application Do not apply below 7 °C. restrictions

Method: Brush

Thinner Clean Water  
(Max vol): (10%)

Nozzle size: N/A

Nozzle N/A  
pressure:

Cleaning Water  
solvent:

Recoat 6 hours @ 20  
interval: deg C

#### SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)

[www.coo-var.co.uk](http://www.coo-var.co.uk)

**LUMINOUS PAINT CLEAR PROTECTIVE****255/W462**

---

**MIXING INSTRUCTIONS:**

Mix well before use.

**APPLICATION CONDITIONS:**

Do not apply below 7 °C.  
As dictated by normal good painting practice.  
In confined spaces, provide adequate ventilation during application and drying.

**PRECEDING COAT:**

Coo-Var Luminous Paint.

**SUBSEQUENT COAT:**

Further coats Coo-Var Luminous Paint Clear Protective.

**REMARKS:**

Do not paint when temperature will be at or below 7 deg C during the painting and drying process.

**HEALTH AND SAFETY:**

See safety data sheet - SDS 10630

**ISSUED:**

20 May 2010

**REVISION:**

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

---

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-var

Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)

[www.coo-var.co.uk](http://www.coo-var.co.uk)